

FORM PTO-1390
(REV. 6-87)U.S. DEPARTMENT OF COMMERCE
PATENT AND TRADEMARK OFFICE

ATTORNEY'S DOCKET NUMBER

**TRANSMITTAL LETTER TO THE UNITED STATES
DESIGNATED/ELECTED OFFICE (DO/EO/US)**

1182-01

09/831926INTERNATIONAL APPLICATION NO.
PCT/JP99/03005INTERNATIONAL FILING DATE
04 June 1999 (04.06.99)PRIORITY DATE CLAIMED
16 November 1998 (16.11.98)

TITLE OF INVENTION

POROUS CONDUCTIVE SHEET AND METHOD FOR PRODUCING THE SAME

APPLICANT(S) FOR DO/EO/US

Mikio Inoue and Takeji Nakae

Applicant herewith submits to the United States Designated/Elected Office (DO/EO/US) the following items under 35 U.S.C. 371:

1. ☒ This express request to immediately begin national examination procedures (35 U.S.C. 371(f)).
2. ☒ The U.S. National Fee (35 U.S.C. 371(c)(1)) and other fees as follows:

CLAIMS	(1) FOR	(2) NUMBER FILED	(3) NUMBER EXTRA	(4) RATE	(5) CALCULATIONS
	TOTAL CLAIMS	41 -20=	21	x \$18.00	\$ 378.00
	INDEPENDENT CLAIMS	2 -3=	0	x \$80.00	
	MULTIPLE DEPENDENT CLAIM(S) (if applicable)			+ \$270.00	270.00
	BASIC NATIONAL FEE (37 CFR 1.492(a)(1)-(4)):				
	<input type="checkbox"/> International preliminary examination fee paid to USPTO (37 CFR 1.482).....\$690.00				
	<input type="checkbox"/> No international preliminary examination fee paid to USPTO (37 CFR 1.482) but international search fee paid to USPTO (37 CFR 1.445(a)(2)).....\$710.00				
	<input type="checkbox"/> Neither international preliminary examination fee (37 CFR 1.482) nor international search fee (37 CFR 1.445(a)(2)) paid to USPTO.....\$1,000.00				
	<input type="checkbox"/> International preliminary examination fee paid to USPTO (37 CFR 1.482) and all claims satisfied provisions of PCT Article 33(2) to (4).....\$ 100.00				
	<input checked="" type="checkbox"/> International Search Report enclosed\$860.00				860.00
	Surcharge of \$_____ for furnishing the National fee or oath or declaration later than <input type="checkbox"/> 20 <input type="checkbox"/> 30 mos. from the earliest claimed priority date (37 CFR 1.482(e)).				\$130.00
	TOTAL OF ABOVE CALCULATIONS				1,508.00
	Reduction by 1/2 for filing by small entity, if applicable. Affidavits must be filed also. (Note 37 CFR 1.9, 1.27, 1.28.)				
	SUBTOTAL				1,508.00
	Processing fee of \$_____ for furnishing the English Translation later than <input type="checkbox"/> 20 <input type="checkbox"/> 30 mos. from the earliest claimed priority date (37 CFR 1.482(f)).				\$130.00
	TOTAL NATIONAL FEE				1,508.00
	Fee for recording the enclosed assignment (37 CFR 1.21(h)).				\$40.00 40.00
	TOTAL FEES ENCLOSED				1,548.00

- a. ☒ A check in the amount of \$1,548.00 to cover the above fees is enclosed.
- b. ☐ Please charge my Deposit Account No. 13-3405 in the amount of \$_____ to cover the above fees.
A duplicate copy of this sheet is enclosed.
- c. ☒ The Commissioner is hereby authorized to charge any additional fees which may be required, or credit any overpayment to Deposit Account No. 13-3405. A duplicate copy of this sheet is enclosed.

JC18 Rec'd PCT/PTO 1 5 MAY 2001

3. A copy of the International Application as filed (35 U.S.C. 371(c)(2))
- ☐ is transmitted herewith (required only if not transmitted by the International Bureau).
 - ☐ is not required, as the application was filed in the United States Receiving Office (RO/US).
 - ☒ has been transmitted by the International Bureau.
4. ☒ A translation of the International Application into English (35 U.S.C. 371(c)(2)).
5. Amendments to the claims of the International Application under PCT Article 19 (35 U.S.C. 371(c)(3))
- ☐ are transmitted herewith (required only if not transmitted by the International Bureau).
 - ☐ have been transmitted by the International Bureau.
6. ☒ A translation of the amendments to the claims under PCT Article 19 (35 U.S.C. 371(c)(3)).
7. ☒ An oath or declaration of the inventor (35 U.S.C. 371(c)(4)).
8. ☐ A translation of the Annexes to the International Preliminary Examination Report under PCT Article 36 (35 U.S.C. 371(c)(5)).

Other document(s) or information included:

9. ☐ An Information Disclosure Statement under 37 C.F.R. 1.97 and 1.98.
10. ☒ Assignment document for recording and a Recordation Form Cover Sheet - Patents Only. Please mail the recorded assignment document to the person whose signature, name and address appears at the bottom of this page.
11. The above checked items are being transmitted
- ☐ before the 18th month publication.
 - ☐ after publication and the Article 20 communication but before 20 months from the priority date.
 - ☐ after 20 months but before 22 months (surcharge and/or processing fee included).
 - ☐ after 22 months (surcharge and/or processing fee included).
- Note:** Petition to revive (37 C.F.R. 1.137(a) or (b)) is necessary if 35 U.S.C. 371 requirements submitted after 22 months *and no proper demand for International Preliminary Examination was made by 19 months from the earliest claimed priority date.*
- ☒ by 30 months and a proper demand for International Preliminary Examination was made by the 19th month from the earliest claimed priority date.
 - ☐ after 30 months but before 32 months and a proper demand for International Preliminary Examination was made by the 19th month from the earliest claimed priority date (surcharge and/or processing fee included).
 - ☐ after 32 months (surcharge and/or processing fee included).
- Note:** Petition to revive (37 C.F.R. 1.137(a) or (b)) is necessary if 35 U.S.C. 371 requirements submitted after 32 months and a proper demand for International Preliminary Examination was made by 19 months from the earliest claimed priority date.
12. At the time of transmittal, the time limit for amending claims under Article 19
- ☐ has expired and no amendments were made.
 - ☐ has not yet expired.
13. ☐ Certain requirements under 35 U.S.C. 371 were previously submitted by the applicant on _____, namely:

SCHNADER HARRISON SEGAL & LEWIS

Date:

May 15, 2001

By:

Austin R. Miller

Austin R. Miller, Reg. No. 16,602
1600 Market Street, 36th Floor
Philadelphia, PA 19103

SPECIFICATION

POROUS CONDUCTIVE SHEET AND METHOD FOR PRODUCING THE SAMETechnical Field

5 The invention relates to a porous conductive sheet and a
method for producing the same. The porous conductive sheet can
be preferably used as an electrode member that is required to have
both gas permeability and electric conductivity. This porous
conductive sheet can be especially preferably used as a current
10 collector in a polymer electrolyte fuel cell.

Background Art

A current collector of a fuel cell is required to have the
function of allowing the materials participating in the electrode
reaction to be diffused and permeate, in addition to the function
15 of collecting the electric current.

Such current collectors of fuel cells are disclosed in JP
06-020710 A, JP 07-326362 A and JP 07-220735 A. The current
collectors disclosed in these documents comprise respectively a
porous carbon plate made of short carbon fibers bound with carbon.

20 The process for producing such a current collector composed
of a porous carbon plate comprises steps of forming an aggregate
of short carbon fibers or precursor fibers thereof, depositing

a resin on the aggregate of short fibers, and baking the aggregate of short fibers having a resin deposited.

The current collector produced by this production process has a low density. So, it has a problem that the binding carbon of the current collector is likely to be destroyed when pressurized in the process of producing an electrode and when pressurized in the process of assembling into a cell.

Furthermore, this production process has a problem that the production cost is too high to produce an inexpensive current collector.

As a method for solving the problem of production cost, JP 07-105957 A or JP 08-007897 A proposes to use a paper-like carbon fiber aggregate produced from short carbon fibers, as a material for constituting a current collector. However, this current collector has a disadvantage that the electric resistance in the thickness direction is high.

As a method for improving the electric resistance in the thickness direction, WO 9827606 proposes a method of adding an electrically conductive filler to a fiber aggregate formed as a non-woven fabric, and discloses that particles of carbon black, graphite or boron carbide can be preferably used as the filler.

However, carbon black particles are likely to come off or run out to leave from the fiber aggregate, since the particle size is very small. If a material for binding the carbon black particles is added in a large quantity for preventing the leaving, the electric resistance becomes high. Graphite particles or boron carbide particles are likely to leave from the fiber aggregate when the fiber aggregate is pressurized, since they are hard. Furthermore, the contact area between the particles and the fibers is so small as to raise the electric resistance.

Further, in JP 56-093265 A or JP 61-032358 A, a porous electrode comprising expanded graphite is disclosed.

However, it turned out that the conventional porous electrode comprising expanded graphite set in a fuel cell as a current collector therein and used continuously under pressurized state is broken i.e. is deformed by creep and holes formed in advance therein deform and decrease in size and as the result the function of allowing the materials participating in the electrode reaction to be diffused and permeate is lost.

It is demanded to develop a current collector that is not only good in the function of collecting the electric current and in the function of allowing the materials participating in the

7:36 AM

electrode reaction to be diffused and permeate, but also unlikely
to be damaged in the current collector production process and in
the process till the current collector is installed in the cell,
and further during using in a cell, i.e., good in handling and
5 small in creep deformation, and also low in electric resistance.
It is also desired that such a current collector can be produced
at a low cost.

Disclosure of the invention

The object of the invention is to solve the above-mentioned
10 problems of current collectors in the prior art.

0001626 054504
F05F50 925T2860

The object of the invention is to provide an inexpensive porous conductive sheet unlikely to allow any component to come off during production and use, unlikely to be broken even if mechanical force acts, and low in electric resistance, and also to provide a production method thereof.

The inventors studied and found that the object could be achieved by using expanded graphite particles as inorganic electrically conductive particles being disposed to form a sheet, while being deposited on inorganic electrically conductive fibers, constituting the porous conductive sheet.

The expanded graphite particles refer to the graphite particles obtained by converting graphite particles into an interlaminar compound using, for example, sulfuric acid or nitric acid, and quickly heating for expanding it. Usually the interlaminar distance in the crystal structure of expanded graphite particles is about 50 to 500 times that of the raw graphite particles.

A porous conductive sheet comprising inorganic electrically conductive particles being disposed to form a sheet while being deposited on inorganic electrically conductive fibers, i.e., a gas permeable electrically conductive sheet, in which some

or all of the inorganic electrically conductive particles are expanded graphite particles, is not known hitherto.

09831926-051501

Expanded graphite particles per se can be highly deformed.
This nature can be expressed by a word, flexibility. This
flexibility can be observed as the form adaptability of the
expanded graphite particles to another body that exists
5 adjacently to the expanded graphite particles.

This form adaptability can be observed when any
pressurization acting on the expanded graphite particles at least
partially overlying on each other makes the particles deformed
mutually and bonded to each other at least partially depending
10 on the pressurizing state.

Furthermore, this form adaptability can also be observed
in the following case. That is, when the expanded graphite
particles and an auxiliary material (for example, conventionally
used inflexible inorganic electrically conductive particles such
15 as carbon black or conventionally used inorganic electrically
conductive fibers such as carbon fibers) used in the case where
the expanded graphite particles are arranged like a sheet in such
a state as to retain the gas permeability are co-pressurized, the
expanded graphite particles are deformed along the external forms
20 of the auxiliary material and bonded to the auxiliary material.

In the observation of the flexibility or form adaptability of expanded graphite particles and the porous conductive sheet formed by using the expanded graphite particles, it can be understood that the object of the invention can be achieved if the inorganic electrically conductive particles used to form the porous conductive sheet are flexible particles.

The porous conductive sheet of the invention for achieving the object of the invention can be provided in either of the following cases.

The first case:

A porous conductive sheet, comprising flexible inorganic electrically conductive particles adhered to inorganic electrically conductive fibers and disposed to form a sheet, wherein at the contact surfaces between the flexible inorganic electrically conductive particles and the inorganic electrically conductive fibers the inorganic electrically conductive fibers deform the surfaces of the flexible inorganic electrically conductive particles in concave and contact with the flexible inorganic electrically conductive particles.

The second case:

A porous conductive sheet, comprising expanded graphite particles adhered to inorganic electrically conductive fibers and disposed to form a sheet, wherein at the contact surfaces between the expanded graphite particles and the inorganic electrically conductive fibers the inorganic electrically fibers deform the surfaces of the expanded graphite particles in concave and contact with the expanded graphite particles.

In either of these cases, for ensuring that the flexible inorganic electrically conductive particles are preferably disposed to form a sheet, the conventional methods for forming porous conductive sheets can be applied. A typical example is to use a sheet-like substrate composed of inorganic electrically conductive fibers for supporting the flexible inorganic

0931926-054501

electrically conductive particles while retaining the gas permeability of the sheet.

The method for producing the porous conductive sheet of the invention comprises steps of forming a sheet comprising inorganic electrically conductive fibers and flexible inorganic electrically conductive particles (expanded graphite particles) and pressurizing the formed sheet in the direction perpendicular to the sheet surface.

The Best Modes for Carrying Out the Invention

The porous conductive sheet has porosity to such an extent as to allow gas permeation in the thickness direction.

As the gas permeability of the sheet in the thickness direction, it is preferable that the pressure loss in the case where air is caused to permeate at 14 cm/sec in the thickness direction in the state where no pressure (face pressure) acts on the sheet surface in the thickness direction is 40 mm Aq or less. More preferable is 15 mm Aq or less, and further more preferable is 5 mm Aq or less. If the pressure loss is large, sufficient gas permeation as a current collector of a fuel cell cannot be obtained.

Since both the electrically conductive fibers and the electrically conductive particles are made of inorganic materials, a current collector excellent in heat resistance, oxidation resistance and dissolving resistance can be obtained.

5 The inorganic electrically conductive fibers that can be preferably used include carbon fibers, metal fibers and ceramic fibers. Among them, carbon fibers and metal fibers are preferable, and especially carbon fibers are preferable. Ceramic fibers are low in electric conductivity, and metal fibers are inferior to
10 carbon fibers since the metal can be dissolved out.

The inorganic electrically conductive particles that can be preferably used together with the flexible inorganic electrically conductive particles (expanded graphite particles) include carbon particles, metal particles and ceramic particles.

15 Among them, carbon particles and metal particles are preferable, and carbon particles are especially preferable. Ceramic particles are low in electric conductivity, and metal particles are inferior to carbon particles since the metal can be dissolved out.

20 It is preferable that the electric resistivity of the inorganic electrically conductive fibers is $0.1 \Omega \cdot \text{cm}$ or less.

More preferable is $0.01 \Omega \cdot \text{cm}$ or less. If the electric resistivity of the inorganic electrically conductive fibers is higher, the electric resistance of the porous conductive sheet becomes higher.

5 Deformation degree Dpf of flexible inorganic electrically conductive particles and inorganic electrically conductive fibers:

The lengths (thicknesses) of the flexible inorganic electrically conductive particles and inorganic electrically
10 conductive fibers in the pressurization direction are measured.

A sample, in which the particles and the fibers are overlaid in the pressurization direction, is prepared. The sample is placed between the sample holding flat faces of two indenters located in opposite to each other in the vertical direction. The

15 indenters are actuated to pressurize the sample, and after the length (sample thickness) in the pressurization direction becomes 80% of that before pressurization, the pressurization is released.

The sample is taken out, and the respective lengths of the flexible inorganic electrically conductive particles and the inorganic

20 electrically conductive fibers in the pressurization direction after completion of pressurization are measured. Then, the

decrement L_p of the length (thickness) of the flexible inorganic electrically conductive particles and the decrement L_f of the length (thickness) of the inorganic electrically conductive fibers due to the pressurization are substituted into the following formula, to obtain the deformation degree D_{pf} .

$$D_{pf} = L_f/L_p$$

It is preferable that the value of the deformation degree D_{pf} of the flexible inorganic electrically conductive particles and the inorganic electrically conductive fibers is 0.1 or less. More preferable is 0.03 or less, and further more preferable is 0.01 or less.

The deformation degree D_{pf} means that the flexible inorganic electrically conductive particles are far more likely to be deformed than the inorganic electrically conductive fibers. If the surface state of the pressurized sample is observed, it can be known that the surfaces of the flexible inorganic electrically conductive particles are deformed and recessed along the form of the inorganic electrically conductive fibers, and that inorganic electrically conductive fibers are positioned in the recesses. Thus, the form adaptability of the flexible inorganic electrically conductive particles can be observed.

This form adaptability means that the contact area between the flexible inorganic electrically conductive particles and another sheet forming material (e.g., inorganic electrically conductive fibers) adjacent to it can be increased.

5 This means that even if an adhesiveness imparting material and a water repellency imparting material, respectively organic materials, exist as required in the porous conductive sheet, form adaptability can be secured between those materials and the inorganic electrically conductive particles.

10 This state assures lowering the electric resistance of the porous conductive sheet, preventing the flexible inorganic electrically conductive particles from coming off and preventing the inorganic electrically conductive fibers from being damaged with pressurization.

15 The porous conductive sheet can contain inflexible inorganic electrically conductive particles such as carbon black powder, graphite powder, metal powder or ceramic powder, but it is preferable that the flexible inorganic electrically conductive particles account for 30 wt% or more of all the inorganic
20 electrically conductive particles. More preferable is 50 wt% or more, and further more preferable is 70 wt% or more.

0991926-051501

The form of the flexible and the inflexible inorganic electrically conductive particles can be close to spheres or rectangular parallelepipeds, or fibrous, like pills or like sheets. The inorganic electrically conductive particles can also be porous.

The porous conductive sheet of the invention can be produced according to any of known conventional porous conductive sheet production methods. Particular production methods are described later in examples.

10 In the case where inorganic electrically conductive particles having a diameter corresponding to 50% or more of the diameter of inorganic electrically conductive fibers are used, a method of producing at first a sheet from the inorganic electrically conductive fibers and the inorganic electrically conductive particles is preferable for obtaining a homogeneous porous conductive sheet. This production method lowers the production cost.

20 In the case where expanded graphite particles are used as the flexible inorganic electrically conductive particles, the expanded graphite particles per se may be used for forming a sheet, or a precursor of the expanded graphite particles may be used to

form a sheet which is heated to change the precursor into expanded graphite particles. The precursor can be, for example, graphite powder treated with sulfuric acid.

The porous conductive sheet can also contain a water repellent polymer, in addition to the inorganic electrically conductive fibers and the inorganic electrically conductive particles. The water repellent polymer is a fluorine resin. Preferably used fluorine resins include polytetrafluoroethylene (PTFE), tetrafluoroethylene-hexafluoropropylene copolymer (FEP), and tetrafluoroethylene-perfluoroalkyl vinyl ether copolymers (PFA). Among them, PTFE is especially preferable.

In the case where the porous conductive sheet is used as a current collector of a fuel cell, water repellency treatment is essential, and in this case, the water repellent polymer has an effect of bonding the inorganic electrically conductive fibers and the inorganic electrically conductive particles to each other. This is useful in view of the strength and electric resistance of the sheet. PTFE, FEP and PFA are high in the water repellency and oxidation resistance that are necessary for a current collector of a fuel cell, and PTFE has an effect of keeping the electric resistance low.

It is preferable that the content of any of these water repellent polymers is 10 to 50 wt% based on the weight of the sheet.

A more preferable range is 15 to 45 wt%, and a further more preferable range is 20 to 40 wt%. If the content is too small,

5 the water repellency and sheet strength become low, and if the content is too large, the electric resistance becomes high.

As the material for imparting water repellency to the sheet, a non-polymeric material can also be used in addition to a polymeric material.

10 The water repellency of a sheet containing a water repellent material is evaluated in reference to the contact angle using water. It is preferable that the contact angle is 120° or more, and more preferable is 135° or more. In the case where the contact angle is low, when a water drop falls on the surface of the sheet,

15 water is less removable from the sheet, and it is observed that the water drop is deposited. If such a sheet is used as a current collector of a fuel cell, water is accumulated on the sheet, and inhibits the diffusion of the materials participating in the electrode reaction.

20 The porous conductive sheet may contain an organic material or the like other than the fluorine resin for such a purpose as

0931926-051501
105750-921360

bonding, in addition to the inorganic electrically conductive fibers and the inorganic electrically conductive particles. The organic materials and the like that can be used in this case include, for example, adhesiveness imparting materials such as a mixture consisting of polyvinyl alcohol and polyvinyl acetate, sodium carboxymethyl cellulose, polyethylene, polypropylene, acrylic resins, phenol resins and epoxy resins.

It is preferable that the content of the organic material or the like other than the fluorine resin contained in the porous conductive sheet in addition to the inorganic electrically conductive fibers and the inorganic electrically conductive particles is 12 wt% or less. More preferable is 8 wt% or less, and further more preferable is 4 wt% or less. If the content of the organic material or the like other than the fluorine resin contained in addition to the inorganic electrically conductive fibers and the inorganic electrically conductive particles is larger, the electric resistance of the sheet becomes higher.

It is most preferable that the porous conductive sheet substantially consists of the inorganic electrically conductive fibers and the inorganic electrically conductive particles only.

In this case, "substantial" means that the content of the

materials other than the inorganic electrically conductive fibers and the inorganic electrically conductive particles is 1 wt% or less. Substantially consisting of the inorganic electrically conductive fibers and the inorganic electrically conductive particles only gives the effects of enhancing the heat resistance and oxidation resistance of the porous conductive sheet and decreasing the matter dissolved out of the electrically conductive sheet.

The porous conductive sheet substantially consisting of the inorganic electrically conductive fibers and the inorganic electrically conductive particles can be produced by a method of producing the porous conductive sheet substantially from the inorganic electrically conductive fibers and the inorganic electrically conductive particles only, or by a method of removing other materials than the inorganic electrically conductive fibers and the inorganic electrically conductive particles from a produced porous conductive sheet using a solvent for dissolving out or heating, etc.

In the case where the porous conductive sheet is used as a current collector of a fuel cell, the porous conductive sheet must have water repellency. For this purpose, the porous

conductive sheet must contain a water repellent material. The water repellent material used for this purpose is as described before.

It is preferable that the content of materials other than the inorganic electrically conductive fibers, the inorganic electrically conductive particles and the water repellent polymeric material in the porous conductive sheet is 8 wt% or less. More preferable is 4 wt% or less. If the content of the materials other than the inorganic electrically conductive fibers, the inorganic electrically conductive particles and the water repellent polymeric material is larger, the electric resistance of the sheet becomes higher.

It is preferable that the porous conductive sheet substantially consists of the inorganic electrically conductive fibers, the inorganic electrically conductive particles and the water repellent material only. In this case, "substantial" means that the content of the materials other than the inorganic electrically conductive fibers, the inorganic electrically conductive particles and the water repellent material is 1 wt% or less. Substantially consisting of the inorganic electrically conductive fibers, the inorganic electrically conductive

particles and the water repellent material only gives effects of enhancing the heat resistance and oxidation resistance of the porous conductive sheet and decreasing the matter dissolved out of the electrically conductive sheet.

5 The porous conductive sheet substantially consisting of the inorganic electrically conductive fibers, the inorganic electrically conductive particles and the water repellent material only can be produced by a method of producing the porous conductive sheet substantially from the inorganic electrically
10 conductive fibers, the inorganic electrically conductive particles and the water repellent material only, or a method of removing the materials other than the inorganic electrically conductive fibers, the inorganic electrically conductive particles and the water repellent material from a produced porous
15 conductive sheet using a solvent for dissolving out or heating, etc.

 It is preferable that the inorganic electrically conductive fibers contained in the porous conductive sheet form an aggregate with a woven fabric structure or a non-woven fabric structure for
20 the purpose of letting the sheet keep shape retention. For obtaining the porous conductive sheet at low cost, it is

preferable that the inorganic electrically conductive fibers have a non-woven fabric structure.

It is preferable that the fiber length of the inorganic electrically conductive fibers in terms of weight average is 3 mm or more. More preferable is 5 mm or more. If the fiber length is too short, the shape retention of the sheet becomes poor, and to enhance the adhesion effect, a material other than the inorganic electrically conductive fibers and the inorganic electrically conductive particles must be used in a large quantity, to raise the electric resistance of the sheet.

In the case where the inorganic electrically conductive fibers have a non-woven fabric structure, it is preferable that the average fiber length is 30 mm or less for obtaining a uniform non-woven fabric structure. More preferable is 15 mm or less, and further more preferable is 9 mm or less.

It is preferable that the diameter of the inorganic electrically conductive particles is 1/2 or more of the diameter of the inorganic electrically conductive fibers. A more preferable diameter is twice or more, and a further more preferable diameter is 8 times or more.

09831926-054501
The inorganic electrically conductive particles have a particle size distribution. It is preferable that 50 wt% or more the particles have diameters (particle size) of 3 μm and more. More preferable is 14 μm and more, and further more preferable is 50 μm and more.

In this case, the diameter of an inorganic electrically conductive particle or an inorganic electrically conductive fiber refers to the average diameter obtained from the major axis and the minor axis.

10 If the diameter of the inorganic electrically conductive particles is too small, more inorganic electrically conductive particles become necessary to connect the inorganic electrically conductive fibers mutually in the thickness direction, to increase the contacts between inorganic electrically conductive
15 particles, lowering the effect of lowering the electric resistance. The flexible inorganic electrically conductive particles are not substantially destroyed or ground due to the pressure acting during pressurization treatment, sheet formation or use, but deformed to be oblate. Keeping the diameter of the
20 flexible inorganic electrically conductive particles in the above range lowers the electric resistance of the sheet.

09831926-054501

The form of the flexible inorganic electrically conductive particles in the porous conductive sheet are oblate, and not always flat, and may be, for example, three-dimensionally curved, since the inorganic electrically conductive fibers may be complicatedly laminated. This is a feature of the flexible inorganic electrically conductive particles.

The electric resistance R of the porous conductive sheet of the invention is measured as follows.

Two test electrode plates, each having a 50 mm wide, 200 mm long and 0.1 mm thick copper foil stuck on one side of a 50 mm wide, 200 mm long and 1.5 mm thick vitreous carbon plate having a smooth flat surface, are prepared. The two test electrode plates are placed with the vitreous carbon plates facing each other, with a substantially uniform clearance kept between them.

At two ends on one side of the two test electrode plates, terminals for current are provided, and at the other two ends on the other side, terminals for voltage are provided.

A cut circular sheet with a diameter of 46 mm is inserted into the clearance and placed at the center of the two test electrode plates. The test electrode plates are moved to let a pressure of 0.98 MPa act on the placed sheet. At the terminals

for current, a current of 1 A is fed to flow between the two test electrode plates. At the terminals for voltage, voltage V (V) at this moment is measured. The value of the measured voltage V is used to obtain resistance R ($\text{m}\Omega \cdot \text{cm}^2$) from the following formula.

$$R = V \times 2.3 \times 2.3 \times \pi \times 1000$$

where π is the ratio of the circumference of a circle to its diameter.

It is preferable that the electric resistance of the porous conductive sheet of the invention is $100 \text{ m}\Omega \cdot \text{cm}^2$ or less. More preferable is $50 \text{ m}\Omega \cdot \text{cm}^2$ or less, and further more preferable is $15 \text{ m}\Omega \cdot \text{cm}^2$ or less.

It is preferable that the electric resistance of the porous conductive sheet containing the water repellent fluorine resin is $150 \text{ m}\Omega \cdot \text{cm}^2$ or less. More preferable is $70 \text{ m}\Omega \cdot \text{cm}^2$ or less, and further more preferable is $30 \text{ m}\Omega \cdot \text{cm}^2$ or less.

The thickness of the porous conductive sheet of the invention is measured as follows.

A sheet (sample) is held between two uniformly thick vitreous carbon plates having smooth surfaces used as indenters. Then, the indenters are moved to apply a uniform face pressure

of 0.98 MPa on the sheet. The pressing pressure in this case is 1800 N. To ensure a uniform face pressure, one of the indenters is supported with a spherical sheet, so that the angle between the pressing surfaces of the top and bottom indenters can be changed.

The indenter clearance L_a formed when a pressing pressure of 1800 N is applied to the top and bottom indenters without any sample held between them and the indenter clearance L_b when the same pressure is applied with a sample held between them are measured, and the difference between both the clearances ($L_b - L_a$) is the thickness L (mm) of the sheet. The indenter clearances are measured at positions where the line passing through the central point of the indenters intersects with both the ends of the indenters using a micro displacement detector, and the mean value of the measured values is adopted as the thickness.

It is preferable that the thickness L of the porous conductive sheet of the invention is in a range of 0.03 to 0.3 mm. A more preferable range is 0.05 to 0.25 mm, and a further more preferable range is 0.07 to 0.2 mm.

If the thickness is smaller, the strength becomes lower, and when the porous conductive sheet is used as a current collector

of a fuel cell, the gas permeability in the face directions becomes lower. If the thickness is larger, the electric resistance becomes higher.

It is preferable that the unit weight of the porous
5 conductive sheet of the invention is in a range of 10 to 220 g/m².
A more preferable range is 20 to 80 g/m², and a further more
preferable range is 30 to 60 g/m².

If the unit weight is smaller, the strength of the sheet becomes
lower, and when the sheet is used as a current collector of a fuel
10 cell, the gas permeability in the face directions becomes lower.
If the unit weight is larger, the electric resistance of the sheet
becomes higher.

It is preferable that the tensile strength of the porous
conductive sheet is 0.49 N/10 mm width or more. More preferable
15 is 1.96 N/10 mm width or more, and further more preferable is 4.9
N/10 mm width or more. If the tensile strength is lower, the sheet
is more likely to be damaged in the sophisticated working of making
the sheet into a current collector of a fuel cell.

The porous conductive sheet of the invention is suitable
20 as a component of a low temperature type fuel cell used in a
temperature range of 300°C or lower, above all, as a current

collector of a polymer electrolyte fuel cell, since it is inexpensive, low in electric resistance and unlikely to be broken with pressurization.

5 A current collector using the porous conductive sheet of the invention and a catalyst layer are disposed in layers, or a current collector using the porous electrolyte sheet of the invention, a catalyst layer and a polymer electrolyte film are disposed in layers, to form a unit for a fuel cell. The unit is assembled into a fuel cell, to make the fuel cell. The fuel cell is suitable as a power supply for driving a movable body such as an automobile or ship, since the current collector used in it is unlikely to be broken, low in electric resistance and inexpensive.

10 In the production of the porous conductive sheet of the invention, the step of pressurizing the sheet at least consisting of the inorganic electrically conductive fibers and the flexible inorganic electrically conductive particles in the direction perpendicular to the sheet surface gives an effect of bonding the flexible inorganic electrically conductive particles to the inorganic electrically conductive fibers. This increases the strength of the obtained sheet, prevents the inorganic

electrically conductive particles from coming off from the sheet and keeps the electric resistance of the sheet low.

Examples

Comparative Example 1:

5 Short PAN carbon fibers cut to a length of 6 mm were dispersed into water and scooped on a wire cloth, to form a sheet. An emulsion composed of a mixture consisting of polyvinyl alcohol and polyvinyl acetate (1:3 as a ratio by weight) as a polymeric material for binding the short carbon fibers was deposited on the
10 sheet, and dried, to obtain a porous conductive sheet.

The unit weight of the porous conductive sheet was 30 g/m², and the content of the polyvinyl alcohol polyvinyl acetate mixture was 22%.

Comparative Example 2:

15 A porous conductive sheet was obtained as described for Comparative Example 1, except that the length of the short PAN carbon fibers was 12 mm and that the content of the polyvinyl alcohol polyvinyl acetate mixture was 5%.

Comparative Example 3:

The porous conductive sheet obtained in Comparative Example 2 was heated in an inactive atmosphere at 800°C, to remove the polyvinyl alcohol polyvinyl acetate mixture.

Comparative Example 4:

5 A carbon fiber cloth ("Torayca" CO6349B produced by Toray Industries, Inc.) was heated in an inactive atmosphere at 800°C, to remove the deposited sizing agent.

Example 1:

Expanded graphite powder (PF Powder 4 produced by Toyo Carbon K.K., bulk density 0.039 g/cm³, average particle size 300 to 500 μm) was sprinkled over both the surfaces of the porous conductive sheet obtained in Comparative Example 1, to be deposited by 11.3 g/m². Then, to bond the expanded graphite powder to the sheet, the sheet was pressurized at a pressure of 098 MPa,
10
15 to produce a porous conductive sheet.

Example 2:

Expanded graphite powder (PF Powder 4 produced by Toyo Carbon K.K., bulk density 0.039 g/cm³, average particle size 300 to 500 μm) was sprinkled over both the surfaces of the porous
20 conductive sheet obtained in Comparative Example 2, to be deposited by 6.5 g/m². Then, to bond the expanded graphite powder

to the sheet, the sheet was pressurized at a pressure of 0.98 MPa,
to produce a porous conductive sheet.

Example 3:

Expanded graphite powder (produced by Toyo Carbon K.K.,
5 bulk density 0.131 g/cm³, average particle size 10 to 20 μm; this
powder was obtained by once forming expanded graphite powder into
a sheet with pressurization and grinding it) was dispersed in
water, to prepare a dispersion. The porous conductive sheet
obtained in Comparative Example 3 was immersed in the dispersion.
10 Then, the sheet was dried to remove water, for producing a porous
conductive sheet. The amount of the expanded graphite powder
deposited on the sheet after drying was 35 g/m².

Example 4:

The amount of the expanded graphite powder deposited on the
15 sheet after drying was changed to 115 g/m² in Example 3. The dried
sheet was pressed at a linear pressure of 50 kg/cm using a roll
press, to produce a porous conductive sheet.

Example 5:

Expanded graphite powder (produced by Toyo Carbon K.K.,
20 bulk density 0.131 g/cm³, average particle size 10 to 20 μm) was
dispersed into water having polyvinyl alcohol dissolved, to

prepare a dispersion. The porous conductive sheet obtained Comparative Example 3 was immersed in the dispersion. Then, the sheet was dried to remove water, for producing a porous conductive sheet. The amount of the expanded graphite powder deposited on the sheet after drying was 32 g/m².

Example 6:

The porous conductive sheet obtained in Example 5 was pressed at a linear pressure of 50 kg/cm using a roll press, to produce a porous conductive sheet.

Example 7:

Expanded graphite powder (PF Powder 4 produced by Toyo Carbon K.K., bulk density 0.039 g/cm³, average particle size 300 to 500 μ m) was sprinkled over both the surfaces of the porous conductive sheet obtained in Comparative Example 4. Then, to bond the expanded graphite powder to the sheet, the sheet was pressurized at a pressure of 0.98 MPa, to produce a porous conductive sheet. The amount of the expanded graphite powder deposited on the sheet was 10 g/m².

Example 8:

Short PAN carbon fibers cut to a length of 12 mm and expanded graphite powder (PF Powder 4 produced by Toyo Carbon K.K., bulk

density 0.039 g/cm², average particle size 300 to 500 μm) were mixed at a ratio by weight of 62:38, and the mixture was dispersed into water. The dispersion was scooped on a wire cloth, to form a sheet with the expanded graphite powder deposited on the short carbon fibers. An emulsion composed of a mixture consisting of polyvinyl alcohol and polyvinyl acetate (mixing ration 1:3) as a polymeric material for binding the short carbon fibers was deposited on the sheet, and the sheet was dried, to produce a porous conductive sheet. The content of the polyvinyl alcohol polyvinyl acetate mixture was 10% based on the amount of the dried sheet. The unit weight of the porous conductive sheet was 43 g/m².

Example 9:

Short PAN carbon fibers cut to a length of 12 mm and expanded graphite powder (PF Powder 4 produced by Toyo Carbon K.K., bulk density 0.039 g/cm³, average particle size 300 to 500 μm) were mixed at a ratio by weight of 1:2, and the mixture was dispersed in a sodium carboxymethyl cellulose aqueous solution. The dispersion was scooped on a wire cloth, to form a sheet with the expanded graphite powder deposited on the short carbon fibers. The sheet was held between two sheets of filter paper and lightly pressurized. Then, the filter paper was removed, to produce a

porous conductive sheet. The unit weight of the porous conductive sheet was 68 g/m², and the sodium carboxymethyl cellulose content was 1%.

Comparative Example 5:

5 Acetylene black powder was dispersed in water having polyvinyl alcohol dissolved. The porous conductive sheet obtained in Comparative Example 3 was coated with the dispersion. Then, the sheet was dried to remove water. The obtained sheet was pressed at a linear pressure of 50 kg/cm using a roll press,
10 to produce a porous conductive sheet. The amount of acetylene black powder deposited on the sheet after drying was 30 g/m².

Data concerning the porous conductive sheets obtained in Examples 1 through 9 and Comparative Examples 1 through 5 are shown in Table 1.

Table 1

	Electrically conductive particles	Unit weight (g/m ²)	Ratio by weight (%)		
			Carbon fibers	Electrically conductive particles	Binding polymer
Example 1	Expanded graphite	42	57	27	16
Example 2	Expanded graphite	31	75	21	4
Example 3	Expanded graphite	59	40	60	0
Example 4	Expanded graphite	140	17	83	0
Example 5	Expanded graphite	64	37	50	13
Example 6	Expanded graphite	64	37	50	13
Example 7	Expanded graphite	216	95	5	0
Example 8	Expanded graphite	43	55	35	10
Example 9	Expanded graphite	68	33	66	1
Comparative Example 1	Nil	30	78	0	22
Comparative Example 2	Nil	25	95	0	5
Comparative Example 3	Nil	24	100	0	0
Comparative Example 4	Nil	206	100	0	0
Comparative Example 5	Acetylene black	57	41	53	6

Table 1 (continued)

	Electric resistance with pressurization at 0.98 MPa ($\text{m}\Omega \cdot \text{cm}^2$)	Thickness with pressurization at 0.98 MPa (mm)	Differential pressure with air permeating at 14 cm/sec (mm Aq)
Example 1	32	0.13	0.5
Example 2	20	0.08	0.4
Example 3	7	0.08	-
Example 4	5	0.11	-
Example 5	31	0.14	-
Example 6	16	0.07	-
Example 7	22	0.25	-
Example 8	51	-	0.6
Example 9	11	-	10
Comparative Example 1	171	0.12	0.4
Comparative Example 2	58	0.08	0.3
Comparative Example 3	25	0.08	-
Comparative Example 4	32	0.24	-
Comparative Example 5	31	0.13	-

From Examples 1 through 9 and Comparative Examples 1 through 4, it can be seen that if expanded graphite particles are added, the electric resistance can be lowered greatly. The differential pressures of the porous conductive sheets obtained in Examples 1, 2, 8 and 9 with permeating air were enough to allow the use of the sheets as current collectors of fuel cells. It can be seen

that especially the porous conductive sheets obtained in Examples 1, 2 and 8 in which the weight of carbon fibers was larger than the weight of expanded graphite particles are not so different from the porous conductive sheets not containing expanded graphite in the comparative examples.

From Example 6 and Comparative Example 5, it can be seen that the effect of expanded graphite particles in lowering the electric resistance is larger than that of acetylene black particles. The reason is that the expanded graphite particles have flexibility or form adaptability.

The electric resistance of the porous conductive sheet obtained in Comparative Example 3 was as low as $25 \text{ m}\Omega \cdot \text{cm}^2$, but the porous conductive sheet obtained in Comparative Example 3 consisting of carbon fibers only was low in the shape retention of the sheet and was liable to be damaged during handling. The electric resistances of the porous conductive sheets containing a binding polymer obtained in Examples 2, 6 and 9 were lower than the electric resistance of the porous conductive sheet not containing any binding polymer obtained in Comparative Example 3, showing the effect of expanded graphite particles in lowering the electric resistance.

When the porous conductive sheet obtained in Comparative Example 3 was pressurized at 29 MPa, numerous carbon fibers were broken. On the contrary, in case of the porous conductive sheet obtained in Example 3, less carbon fibers were broken, and in the cases of the porous conductive sheets obtained in Examples 4, 5 and 6, few carbon fibers were broken. It is considered that the presence of expanded graphite particles and polyvinyl alcohol eased the concentration of pressing pressure among carbon fibers.

Example 10:

Short PAN carbon fibers cut to a length of 12 mm and expanded graphite powder (PF Powder 4 produced by Toyo Carbon K.K., bulk density 0.039 g/cm³, average particle size 300 to 500 μ m) were mixed at a ratio by weight of 1:1, and the mixture was dispersed into a sodium carboxymethyl cellulose aqueous solution. The dispersion was scooped on a wire cloth, to form a sheet with the expanded graphite powder deposited on the short carbon fibers. The sheet was held between two sheets of filter paper and lightly pressurized for the purpose of removing water. The filter paper was removed, and the sheet was dried. The dried sheet was pressed at a linear pressure of 50 kg/cm using a roll press, to produce a porous conductive sheet.

Examples 11, 12 and 13:

Short PAN carbon fibers cut to a length of 12 mm and expanded graphite powder (PF Powder 4 produced by Toyo Carbon K.K., bulk density 0.039 g/cm³, average particle size 300 to 500 μ m) were mixed at a ratio by weight of 1:1, and the mixture was dispersed into a sodium carboxymethyl cellulose aqueous solution. The dispersion was scooped on a wire cloth, to form a sheet with the expanded graphite powder deposited on the short carbon fibers. The sheet was held between two sheets of filter paper and lightly pressurized for the purpose of removing water. The filter paper was removed, and the sheet was dried. The dried sheet was pressed at a linear pressure of 50 kg/cm using a roll press, to produce a porous conductive sheet.

Furthermore, the porous conductive sheet was heat-treated in air at 200°C for 30 minutes. The heat-treated sheet was impregnated with a PTFE dispersion (Polyfuron PTFE Dispersion produced by Daikin Industries, Ltd.). The impregnated sheet was held between two sheets of filter paper and lightly pressurized. Then, the filter paper was removed from the sheet, and the sheet was dried. The dried sheet was heat-treated at 370°C for 10 minutes, while being pressurized at 12 kgf/cm², to produce a porous

conductive sheet. The concentration of the PTFE dispersion used was 15% in Example 11, 20% in Example 12, and 24% in Example 13.

Example 14:

Short PAN carbon fibers cut to a length of 12 mm and expanded
5 graphite powder (produced by Toyo Carbon K.K., bulk density 0.14
g/cm³, average particle size 100 to 200 μ m) were mixed at a ratio
by weight of 1:1, and the mixture was dispersed into a sodium
carboxymethyl cellulose aqueous solution. The dispersion was
scooped on a wire cloth, to form a sheet with the expanded graphite
10 powder deposited on the short carbon fibers. The sheet was held
between two sheets of filter paper and lightly pressurized for
the purpose of removing water. Then, the filter paper was removed,
and the sheet was dried. The dried sheet was pressed using a roll
press, to produce a porous conductive sheet. The clearance of
15 the roll press was adjusted to 220 μ m, 170 μ m and 120 μ m, for
pressing three times.

Examples 15 and 16:

Short PAN Carbon fibers cut to a length of 12 mm and expanded
graphite powder (produced by Toyo Carbon K.K., bulk density 0.14
20 g/cm³, average particle size 100 to 200 μ m) were mixed at a ratio
by weight of 1:1, and the mixture was dispersed into a sodium

carboxymethyl cellulose aqueous solution. The dispersion was scooped on a wire cloth, to form a sheet with the expanded graphite powder deposited on the short carbon fibers. The sheet was held between two sheets of filter paper and lightly pressurized for the purpose of removing water. Then, the filter paper was removed, and the sheet was dried. The dried sheet was pressed using a roll pressed, to produce a porous conductive sheet. In Example 15, the clearance of the roll press was adjusted to 220 μm , 170 μm and 120 μm , for pressing three times. In Example 16, the produced porous conductive sheet was not pressed using a roll press.

Furthermore, the porous conductive sheet was heat-treated in air at 200°C for 30 minutes, and impregnated with an FEP dispersion (Neofuron FEP Dispersion produced by Daikin Industries, Ltd.). The sheet was held between two sheets of filter paper and lightly pressurized. Then, the filter paper was removed from the sheet, and the sheet was dried. The dried sheet was pressurized at 0.15 kgf/cm² while being heat-treated at 310°C for 3 hours, to produce a porous conductive sheet.

Example 17:

A porous conductive sheet was produced as described for Example 11, except that short PAN carbon fibers cut to a length of 12 mm, expanded graphite powder (produced by Toyo Carbon K.K., bulk density 0.14 g/cm³, average particle size 100 to 200 μm) and a PTFE dispersion (Polyfuron PTFE Dispersion produced by Daikin Industries, Ltd.) were used.

Examples 18 and 19

The porous conductive sheet of Example 18 was produced as described for Example 15, and the porous conductive sheet of Example 19 was produced as described for Example 16, except that short PAN carbon fibers cut to a length of 12 mm, expanded graphite powder (produced by Toyo Carbon K.K., bulk density 0.14 g/cm³, average particle size 100 to 200 μm) and an FEP dispersion (Neofuron FEP Dispersion produced by Daikin Industries, Ltd.) were used.

Example 20:

Short PAN carbon fibers cut to a length of 12 mm and expanded graphite powder (produced by Toyo Carbon K.K., bulk density 0.14 g/cm³, average particle size 100 to 200 μm) were mixed at a ratio by weight of 1:1, and the mixture was dispersed into a sodium carboxymethyl cellulose. The dispersion was scooped on a wire

09831926-054504
T05T0926T0860

cloth, to form a sheet with the expanded graphite powder deposited on the short carbon fibers. The sheet was held between two sheets of filter paper and lightly pressurized for the purpose of removing water. Then, the filter paper was removed, and the sheet was dried. The dried sheet was pressed using a roll press, to produce a porous conductive sheet. The clearance of the roll press was adjusted to 220 μm , 170 μm and 120 μm for pressing three times.

Furthermore, the porous conductive sheet was heat-treated in air at 200 $^{\circ}\text{C}$ for 30 minutes, and impregnated with a polyvinylidene fluoride (PVDF) N-methyl-2-pyrrolidone solution (concentration 10 wt%). The impregnated sheet was held between two sheets of filter paper and lightly pressurized. Then, from the sheet, the filter paper was removed, and the sheet was dried. The dried sheet was pressurized at 0.15 kgf/cm^2 while being heat-treated at 200 $^{\circ}\text{C}$ for 3 hours, to produce a porous conductive sheet.

Data concerning the porous conductive sheets obtained in Examples 10 through 13 are shown in Table 2. Data concerning the porous conductive sheets obtained in Examples 14 through 16 are

shown in Table 3. Data concerning the porous conductive sheets obtained in Examples 17 through 20 are shown in Table 4.

Table 2

	Electrically conductive particles	Unit weight (g/m ²)	Ratio by weight (%)			
			Carbon fibers	Electrically conductive particles	Binding polymer	
					CMC	PTFE
Example 10	Expanded graphite	57	49	49	2	0
Example 11	Expanded graphite	76	38	38	1	23
Example 12	Expanded graphite	73	33	33	1	33
Example 13	Expanded graphite	92	29	30	1	40

Table 2 (continued)

	Electric resistance with pressurization at 0.98 MPa (m Ω · cm ²)	Thickness with pressurization at 0.98 MPa (mm)	Differential pressure with air permeating at 14 cm/sec. (mmAq)	Contact angle (°)
Example 10	11	0.095	1.9	
Example 11	23	0.11	4.2	132
Example 12	28	0.097	3.2	127
Example 13	34	0.10	3.8	135

Table 3

	Electrically conductive particles	Unit weight (g/m ²)	Ratio by weight (%)			
			Carbon fibers	Electrically conductive particles	Binding polymer	
					CMC	FEP
Example 14	Expanded graphite	70	49	49	2	0
Example 15	Expanded graphite	86	37	37	1	25
Example 16	Expanded graphite	91	36	36	1	27

Table 3 (continued)

	Electric resistance with pressurization at 0.98 MPa (m Ω · cm ²)	Thickness with pressurization at 0.98 MPa (mm)	Differential pressure with air permeating at 14 cm/sec. (mmAq)
Example 14	13	0.090	3.2
Example 15	54	0.10	5.1
Example 16	86	0.235	1.4

Table 4

	Electrically conductive particles	Binding polymer		Unit weight (g/m ²)	Ratio by weight (%)			
		1	2		Carbon fibers	Electrically conductive particles	Binding polymer	
							1	2
Example 17	Expanded graphite	CMC	PTFE	80	31	47	1	21
Example 18	Expanded graphite	CMC	FEP	64	37	55	1	7
Example 19	Expanded graphite	CMC	FEP	84	31	47	1	21
Example 20	Expanded graphite	CMC	PVDF	80	32	47	1	20

Table 4 (continued)

	Electric resistance with pressurization at 0.98 MPa (m Ω · cm ²)	Thickness with pressurization at 0.98 MPa (mm)	Differential pressure with air permeating at 14 cm/sec. (mmAq)	Tensile strength upper (kgf/10 mm width) lower (N/10 mm width)	Contact angle (°)
Example 17	25	0.11	3.0	0.04 0.4	141
Example 18	31	0.12	2.0		
Example 19	52	0.12	4.6	1.2 12	141
Example 20	28	0.12	4.4	1.3 13	

Industrial Applicability

The porous conductive sheet of the invention is low in electric resistance and unlikely to cause any component of it to be broken or come off when pressurized. Components of it are little oxidized or dissolved out. The production cost is low. The porous conductive sheet of the invention is small in voltage drop and breakage and is suitable as a long life current collector of a fuel cell.

FOI 9267E860

Claims

1. (Deleted)

2. (Deleted)

3. (Amended) A porous conductive sheet comprising flexible

5 inorganic electrically conductive particles adhered to inorganic

electrically conductive fibers and disposed to form a sheet,

wherein the surfaces of the inorganic electrically conductive

particles are recessed at the contact faces between the inorganic

electrically conductive fibers and the inorganic electrically

10 conductive particles.

4. (Amended) A porous conductive sheet according to claim

3, which includes a water repellent material.

5. (Amended) A porous conductive sheet according to claim

3, which substantially consists of the inorganic electrically

15 conductive fibers and the inorganic electrically conductive

particles only.

6. A porous conductive sheet according to claim 4, which

substantially consists of the inorganic electrically conductive

fibers, the inorganic electrically conductive particles and the

20 water repellent material only.

SECRET

7. (Amended) A porous conductive sheet according to any one of claims 3 through 6, wherein the length of the inorganic electrically conductive fibers is 3 mm or more.

8. (Amended) A porous conductive sheet according to any one of claims 3 through 7, wherein the diameter of the inorganic electrically conductive particles is 1/2 or more of the diameter of the inorganic electrically conductive fibers.

9. (Amended) A porous conductive sheet according to any one of claims 3 through 8, wherein the inorganic electrically conductive fibers are carbon fibers.

10. (Amended) A porous conductive sheet according to any one of claims 3 through 9, which has an electric resistance of 150 $m\Omega \cdot cm^2$ or less.

11. (Amended) A porous conductive sheet according to any one of claims 3 through 10, which has a thickness of 0.03 to 0.3 mm and a unit weight of 10 to 220 g/m^2 .

12. (Amended) A porous conductive sheet according to any one of claims 3 through 11, which has a tensile strength of 0.49 N/10 mm width or more.

13. (Deleted)

1/15/84

14. (Deleted)

15. (Amended) A porous conductive sheet comprising expanded graphite particles adhered to inorganic electrically conductive fibers and disposed to form a sheet, wherein the surfaces of the expanded graphite particles are recessed at the contact faces between the inorganic electrically conductive fibers and the expanded graphite particles.

16. (Amended) A porous conductive sheet according to claim 15, which further contains a water repellent material.

17. (Amended) A porous conductive sheet according to claim 15, which substantially consists of the inorganic electrically conductive fibers and the inorganic electrically conductive particles only.

18. A porous conductive sheet according to claim 16, which substantially consists of the inorganic electrically conductive fibers, the inorganic electrically conductive particles and the water repellent material only.

19. (Amended) A porous conductive sheet according to claim 15, wherein the length of the inorganic electrically conductive fibers is 3 mm or more.

09831926.051501
T05T50.925T0260

20. (Amended) A porous conductive sheet according to claim 15, wherein the diameter of the inorganic electrically conductive particles is 1/2 or more of the diameter of the inorganic electrically conductive fibers.

5 21. (Amended) A porous conductive sheet according to any one of claims 15 through 20, wherein the inorganic electrically conductive fibers are carbon fibers.

22. (Amended) A porous conductive sheet according to any one of claims 15 through 21, which has an electric resistance of 150
10 $\text{m}\Omega \cdot \text{cm}^2$ or less.

23. (Amended) A porous conductive sheet according to any one of claims 15 through 22, which has a thickness of 0.03 to 0.3 mm and a unit weight of 10 to 220 g/m^2 .

24. (Amended) A porous conductive sheet according to any one
15 of claims 15 through 23, which has a tensile strength of 0.49 N/10 mm width.

25. (Amended) A porous conductive sheet according to any one of claims 1 through 12 and claims 15 through 24, which is used as a current collector of a fuel cell.

26. (Amended) A current collector for a fuel cell,
comprising the use of the porous conductive sheet as set forth
in any one of claims 1 through 12 and claims 15 through 24.

27. A unit for a fuel cell, comprising the current collector as set forth in claim 26, provided with a catalyst layer.

28. A unit for a fuel cell, comprising the current collector as set forth in claim 26, provided with a catalyst layer and a

5 polymer electrolyte film.

29. A fuel cell, comprising the unit as set forth in claim 27 or 28.

30. A movable body, mounted with the fuel cell as set forth in claim 29.

10 31. (Amended) A method for producing the porous conductive sheet as set forth in any one of claims 1 through 12 and claims 15 through 24, comprising the step of pressurizing the porous conductive sheet in the direction perpendicular to the surface of the sheet in the step of forming the porous conductive sheet.

ABSTRACT

A porous conductive sheet comprising at least inorganic electrically conductive fibers and inorganic electrically conductive particles, wherein the inorganic electrically
5 conductive particles are flexible. A porous conductive sheet, wherein the inorganic electrically conductive particles are expanded graphite.

The porous conductive sheet is less likely to cause its members to be damaged or to come off in the step of forming the
10 sheet or in the process of assembling the sheet into a cell, than the conventional porous conductive sheets. It is also lower in production cost.

00331925-051501
T05759-9257E860

Express Mail Label EL618700614US

- ☐ Original Application
- ☒ PCT National Application
- ☐ U.S. Designated Office
- ☐ Continuation or Divisional Application
- ☐ Continuation-in-Part Application

**COMBINED DECLARATION,
POWER OF ATTORNEY AND PETITION**

As a below named inventor, I hereby declare that:

My residence, post office address and citizenship are as stated below next to my name,

I believe I am the original, first and sole inventor (if only one name is listed below) or an original, first and joint inventor (if plural names are listed below) of the subject matter which is claimed and for which a patent is sought on the invention entitled POROUS CONDUCTIVE SHEET AND METHOD FOR PRODUCING THE SAME

☐ which is described in the specification and claims

☐ attached hereto.

☐ filed on _____

Application Serial No. _____

and was amended on _____

(if applicable)

☒ which is described in International Application No. PCT/JP99/03005

filed June 4, 1999 and as amended on _____

November 24, 2000 (if any),

which I have reviewed and for which I solicit a United States patent.

I hereby state that I have reviewed and understand the contents of the above-identified specification, including the claims, as amended by any amendment referred to above.

I acknowledge the duty to disclose information which is material to the examination of this application in accordance with Title 37, Code of Federal Regulations, §1.56.

I do not know and do not believe that this invention was ever known or used in the United States before my or our invention thereof or patented or described in any printed publication in any country before my or our invention thereof or more than one year prior to this application or said international application, or in public use or on sale in the United States of America more than one year prior to this application or said international application, or that the invention has been patented or made the subject of an inventor's certificate issued before the date of this application or said international application in any country foreign to the United States of America on an application filed by me or my legal representatives or assigns more than twelve months prior to this application or said international application, or that any application for patent or inventor's certificate on this invention has been filed in any country foreign to the United States of America prior to this application or said international application by me or my legal representatives or assigns except as identified below.

COMBINED DECLARATION, POWER OF ATTORNEY AND PETITION

(Page 2)

Attorney Docket No. 1182-01

I hereby claim foreign priority benefits under Title 35, United States Code, §119(a)-(d) or §365(b) of any foreign application(s) for patent or inventor's certificate, or §365(a) of any PCT International Application which designated at least one country other than the United States of America, listed below and have also identified below any foreign application(s) for patent or inventor's certificate, or of any PCT International Application having a filing date before that of the application on which priority is claimed:

Number	Country	Date of Filing (day,month,year)	Priority Claimed
HEI-10-325264	Japan	16.11.98	<input checked="" type="checkbox"/> yes <input type="checkbox"/> no
			<input type="checkbox"/> yes <input type="checkbox"/> no
			<input type="checkbox"/> yes <input type="checkbox"/> no
			<input type="checkbox"/> yes <input type="checkbox"/> no
			<input type="checkbox"/> yes <input type="checkbox"/> no

I hereby claim the benefit under Title 35, United States Code, §119(e) or §120 (as applicable) of any United States application(s), or §365(c) of any PCT International Application designating the United States of America, listed below and, insofar as the subject matter of each of the claims of this application is not disclosed in the prior United States or PCT International Application(s) in the manner provided by the first paragraph of Title 35, United States Code, §112:

(Application Serial No.)(Filing Date)(Status) (patented, pending, abandoned)(Application Serial No.)(Filing Date)(Status) (patented, pending, abandoned)

POWER OF ATTORNEY: As a named inventor, I hereby appoint the registered attorneys listed under Customer No. 022469 and the following registered attorneys to prosecute this application and transact all business in the United States Patent and Trademark Office connected therewith:

13 T. Daniel Christenbury Reg. No. 31,750
 Guy T. Donatiello Reg. No. 33,167
 Paul A. Taufer Reg. No. 35,703
 James A. Drobile Reg. No. 19,690
 Austin R. Miller Reg. No. 16,602
 Gerard J. Weiser Reg. No. 19,763
 Joan T. Kluger Reg. No. 38,940

Patrick J. Farley Reg. No. 42,524
 Michael A. Patane Reg. No. 42,982
 David A. Sasso Reg. No. 43,084
 Robert A. McKinley Reg. No. 43,793
 Sharon Fenick Reg. No. 45,269
 Stewart M. Wiener Reg. No. 46,201

SEND CORRESPONDENCE TO:

IP Department
 Schnader Harrison Segal & Lewis
 36th Floor, 1600 Market Street
 Philadelphia, PA 19103

**22469**

PATENT TRADEMARK OFFICE

DIRECT TELEPHONE CALLS TO
ATTORNEY OF RECORD AT:

(215) 563-1810

COMBINED DECLARATION, POWER OF ATTORNEY AND PETITION

(Page 3)

Attorney Docket No. 1182-01

I hereby petition for grant of a United States Letters Patent on this invention.

I hereby declare that all statements made herein of my own knowledge are true and that all statements made on information and belief are believed to be true; and further that these statements were made with the knowledge that willful false statements and the like so made are punishable by fine or imprisonment, or both, under Section 1001 of Title 18 of the United States Code and that such willful false statements may jeopardize the validity of the application or any patent issued thereon.

1. FULL NAME OF SOLE OR FIRST INVENTOR Mikio INOUE		INVENTOR'S SIGNATURE <i>Mikio Inoue</i>	DATE <i>May 7, 2001</i>
RESIDENCE Shiga, Japan <i>JPX</i>		CITIZENSHIP Japan	
POST OFFICE ADDRESS 13-1, Sonoyama 2-chome, Otsu-shi, Shiga 520-0842 Japan			
2. FULL NAME OF JOINT INVENTOR, IF ANY Takeji NAKAE		INVENTOR'S SIGNATURE <i>Takeji Nakae</i>	DATE <i>May 7, 2001</i>
RESIDENCE Shiga, Japan <i>JPX</i>		CITIZENSHIP Japan	
POST OFFICE ADDRESS 29-23, Jinryou 2-chome, Otsu-shi, Shiga 520-2132 Japan			
3. FULL NAME OF ADDITIONAL JOINT INVENTOR, IF ANY		INVENTOR'S SIGNATURE	DATE
RESIDENCE		CITIZENSHIP	
POST OFFICE ADDRESS			
4. FULL NAME OF ADDITIONAL JOINT INVENTOR, IF ANY		INVENTOR'S SIGNATURE	DATE
RESIDENCE		CITIZENSHIP	
POST OFFICE ADDRESS			
5. FULL NAME OF ADDITIONAL JOINT INVENTOR, IF ANY		INVENTOR'S SIGNATURE	DATE
RESIDENCE		CITIZENSHIP	
POST OFFICE ADDRESS			
6. FULL NAME OF ADDITIONAL JOINT INVENTOR, IF ANY		INVENTOR'S SIGNATURE	DATE
RESIDENCE		CITIZENSHIP	
POST OFFICE ADDRESS			
7. FULL NAME OF ADDITIONAL JOINT INVENTOR, IF ANY		INVENTOR'S SIGNATURE	DATE
RESIDENCE		CITIZENSHIP	
POST OFFICE ADDRESS			